



#### PRODUCT SPECIFICATIONS

Pipe Type	All rigid PVC
Cement Uses	For pool, spa, water gardening, irrigation and other applications
Maximum Diameter	6 inches (160mm) 4 inches (110mm), Schedule 80
Color	Clear
Relative Set Time	Fast
Body	Medium Bodied
Performance Specification	ASTM D2564 SCAQMD Rule 1168/316A NSF/ANSI Standard 14 and 61 Uniform Plumbing Code
Brookfield Viscosity	Minimum 500 cps
Specific Gravity	0.947 ± 0.04
VOC Emissions	416 g/L
Shelf Life	3 Years
LEED Compliant	Credit can be earned per LEED® (Leadership in Energy and Environmental Design), IEQ Credit 4.1

## FLEX PRO™ PVC CEMENT

Christy's® FLEX PRO™ PVC CEMENT is a medium bodied, fast set, high strength PVC solvent cement designed for PVC pipe sizes with interference fit thru 6 inches (160 mm) diameter, Schedule 80 through 4 inches (110 mm) diameter.

- Meets the unique challenges of flexible joints. High performance solvent cement specially formulated to form flexible, high-strength water resistant joints in both flex-to-flex and flex-to-fitting applications
- Uniquely resilient to vibrations common with spa and swimming pool installations.
- Suitable for irrigation (flexible risers and drop lines), pool, spa, water gardening and other applications.
- Ultra low VOC emissions. Meets SCAQMD Rule 1168/316A.
- High strength performance. Meets ASTM D2564 and the Uniform Plumbing Code. Certified by NSF International.



PW-G/DW/SW  
U.P. CODE

**WARNING:** Cancer - [www.P65Warnings.ca.gov](http://www.P65Warnings.ca.gov)

#### SPECIAL PRECAUTION

Christy's solvent products must never be used in plastic piping system using or being tested by compressed air or gases; including air-over-water booster. Do not use in conjunction with flue gas ventilation systems.

Do not use a dry granular calcium hypochlorite as a disinfecting material for water purification in potable water piping systems. The introduction of granules or pellets of calcium hypochlorite with solvent cements and primers (including their vapors) may result in a violent chemical reaction if a water solution is not used. It is advisable to purify lines by pumping chlorinated water into the piping system – this solution will be nonvolatile. Furthermore, dry granular calcium hypochlorite should not be stored or used near solvent cements and primers.

This product is intended for use by skilled individuals at their own risk. Installers should verify for themselves that they can make satisfactory joints under varying conditions. Detailed directions on making solvent cemented joints are printed on the container label. It is highly recommended that the installer review the instructions supplied by the pipe and fitting manufacturer.

**Refer to the current Safety Data Sheet for additional safety precautions, first-aid, storage, handling, transportation and disposal information.**

**Storage temperature: 40°F (5°C) – 110°F (43°C)**

**Refer to website for complete Terms and Conditions.**

