



GRAY MEDIUM BODIED PVC CEMENT

Christy's® GRAY MEDIUM BODIED PVC CEMENT is a professional grade, medium bodied, fast set, high strength PVC solvent cement designed for PVC pipe sizes thru 6" (150 mm) all schedules and classes. Schedule 80 thru 4" (110 mm).

- Professional grade, high strength PVC cement specially formulated to join pipe and fitting surfaces and create a strong quick bond.
- Medium bodied formulation delivers good gap filling capacity between pipe & fittings.
- Gray color enables visual confirmation that cement has been applied.
- Ultra low VOC emissions. Meets SCAQMD Rule 1168/316A.
- GreenGuard Gold certified. Visit the UL Sustainable Database at www.spot.ul.com to find all the sustainable credits covered by UL GreenGuard Gold.
- High strength performance. Meets ASTM D2564, CSA B137.3 / B181.2 and the Uniform Plumbing Code. Certified by NSF International.

PRODUCT SPECIFICATIONS

| | |
|---------------------------|--|
| Pipe Type | All rigid PVC |
| Cement Uses | For PVC pipe and fitting applications; potable water, pressure, non-pressure, conduit, drain, DWV, and sewer |
| Maximum Diameter | 6 inches (160mm) 4 inches (110mm), Schedule 80 |
| Color | Gray |
| Relative Set Time | Fast |
| Body | Medium Bodied |
| Performance Specification | ASTM D2564 SCAQMD Rule 1168/316A NSF/ANSI Standard 14 and 61 Uniform Plumbing Code CSA B137.3 & CSA B181.2 |
| Brookfield Viscosity | Minimum 500 cps |
| Specific Gravity | 0.92 ± 0.04 |
| VOC Emissions | 405 g/L |
| Shelf Life | 3 Years |
| LEED Compliant | Credit can be earned per LEED® (Leadership in Energy and Environmental Design), IEQ Credit 4.1 |



PW-G/DWV/SW
U.P. CODE



SPECIAL PRECAUTION

Christy's solvent products must never be used in plastic piping system using or being tested by compressed air or gases; including air-over-water booster. Do not use in conjunction with flue gas ventilation systems.

Do not use a dry granular calcium hypochlorite as a disinfecting material for water purification in potable water piping systems. The introduction of granules or pellets of calcium hypochlorite with solvent cements and primers (including their vapors) may result in a violent chemical reaction if a water solution is not used. It is advisable to purify lines by pumping chlorinated water into the piping system – this solution will be nonvolatile. Furthermore, dry granular calcium hypochlorite should not be stored or used near solvent cements and primers.

This product is intended for use by skilled individuals at their own risk. Installers should verify for themselves that they can make satisfactory joints under varying conditions. Detailed directions on making solvent cemented joints are printed on the container label. It is highly recommended that the installer review the instructions supplied by the pipe and fitting manufacturer.

Refer to the current Safety Data Sheet for additional safety precautions, first-aid, storage, handling, transportation and disposal information.

Storage temperature: 40°F (5°C) – 110°F (43°C)

Refer to website for complete Terms and Conditions.



IPS Corporation
455 W. Victoria St.,
Compton, CA 90220
(800) 888-8312
www.tchristy.com