



RED HOT POOL PRO™

Christy's® RED HOT POOL PRO™ is a high-performance, blue fade to clear, medium bodied, very fast setting PVC solvent cement for PVC pipe sizes thru 6" (150 mm) all schedules and classes. Schedule 80 thru 4" (110 mm).

- Designed for pool, spa and whirlpool applications.
- Thick, medium bodied viscosity allow cement to grip on pipe and fittings fast with fewer drips. Pipe joint sets very fast.
- Initial blue color enables visual confirmation that cement has been applied. Cement fades to clear after exposure to sunlight for clean joints in exposed installations.
- Ultra low VOC emissions. Meets SCAQMD Rule 1168/316A.
- GreenGuard Gold certified. Visit the UL Sustainable Database at www.spot.ul.com to find all the sustainable credits covered by UL GreenGuard Gold.
- High strength performance. Meets ASTM D2564 and the Uniform Plumbing Code. Certified by NSF International.

PRODUCT SPECIFICATIONS

Pipe Type	All rigid PVC
Cement Uses	For PVC pipe and fitting applications; pool & spa, potable water, pressure, non-pressure, conduit, drain, duct, DWV and sewer
Maximum Diameter	6 inches (160mm) 4 inches (110mm), Schedule 80
Color	Blue fade to clear
Relative Set Time	Very Fast
Body	Medium Bodied
Performance Specification	ASTM D2564 SCAQMD Rule 1168/316A NSF/ANSI Standard 14 and 61 Uniform Plumbing Code
Brookfield Viscosity	Minimum 500 cps
Specific Gravity	0.926 ± 0.04
VOC Emissions	423 g/L
Shelf Life	3 Years
LEED Compliant	Credit can be earned per LEED® (Leadership in Energy and Environmental Design), IEQ Credit 4.1



PW-G/DWW/SW
U.P. CODE



WARNING: Cancer - www.P65Warnings.ca.gov

SPECIAL PRECAUTION

Christy's solvent products must never be used in plastic piping system using or being tested by compressed air or gases; including air-over-water booster. Do not use in conjunction with flue gas ventilation systems.

Do not use a dry granular calcium hypochlorite as a disinfecting material for water purification in potable water piping systems. The introduction of granules or pellets of calcium hypochlorite with solvent cements and primers (including their vapors) may result in a violent chemical reaction if a water solution is not used. It is advisable to purify lines by pumping chlorinated water into the piping system – this solution will be nonvolatile. Furthermore, dry granular calcium hypochlorite should not be stored or used near solvent cements and primers.

This product is intended for use by skilled individuals at their own risk. Installers should verify for themselves that they can make satisfactory joints under varying conditions. Detailed directions on making solvent cemented joints are printed on the container label. It is highly recommended that the installer review the instructions supplied by the pipe and fitting manufacturer.

Refer to the current Safety Data Sheet for additional safety precautions, first-aid, storage, handling, transportation and disposal information.

Storage temperature: 40°F (5°C) – 110°F (43°C)

Refer to website for complete Terms and Conditions.

